

TECHNICAL SHEET: 2404

4:1 CLEARCOAT

DESCRIPTION AND FIELDS OF APPLICATION

KMK 2404 4:1 CLEARCOAT is ideal for partial or complete repairs.

Due to its viscosity and solvent selection, it's easy to apply even at low pressures.

It is easy to avoid excessive spraying.

Once applied, dust dry and air curing are quick.

For its characteristics this product is easy to polish.

VOC: 4.9 lb/gal Application (100:25 vol)

TECHNICAL DATA

Nature:	Acrylic 2K		
Specific weight:	7.5 lb/gal @ 68ºF		
Color:	Colourless		
Viscosity CF/4:	15 sec @ 68ºF		
Dry film thickness:	2.0 – 2.2 mils 2 coats		
Coverage:	360-400 ft²/gal		
Safety data:	Refer to the safety sheet		

SURFACE PREPARATION



Apply KMK 2404 4:1 CLEARCOAT on the base coat after the flash off time recommended by the manufacturer.

CAUTIONS

- * Humidity affects clearcoat components so the application equipment should be absolutely dry.
- * Close the hardener container immediately after use.
- * When relative humidity is higher than 70% and/or temperatures lower than +50°F it is recommended to dry at 140°F.
- * Store the product in a ventilated place far from direct exposure to sunlight. Keep between +41°F and +86°F.



TECHNICAL SHEET: 2404

4:1 CLEARCOAT

PROCESSING

MIXING RATIO APPLICATION METHOD

KMK 2404 4:1 CLEARCOAT	AVBVC		S	A B
			68	°F
KMK 4901 Normal Hardener	100:25:0-5	4:1	15 sec F/4	4 hrs

	Inches	psi	inches		<u>}</u>
>1 1/4	0.047 - 0.055	29.0 - 36.3	5.9 – 7.9		
***	0.059 - 0.067	29.0 - 43.5	5.9 – 7.9	2-3	3-5 min
≱]I. HVLP	0.047 - 0.055	29.0 - 36.3	3.9		

DRYING TIMES

68° F 140° F IR - OC

	<u> </u>	R		9	
KMK 4901 Normal Hardener	9 min	3.5 hrs	5 hrs	8 hrs	8 hrs

	R
KMK 4901 Normal Hardener	20-25 min

	FLASH OFF	FULL BAKE
BLACK	3 min	5 min
WHITE	4 min	6 min

TOOLS CLEANING

Use a cleaning thinner before the pot life has expired.

Technical indications and advices are based on our own experiences.

We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained.

Kimakem srl

Via Don G. Fortuna 82 36050 Monteviale – Vicenza (Italy) info@kimakem.com www.kmk-refinish.com