


# QUICK GUIDE TO THE CLEAR COATING CHOICE



SKU	<b>2505</b>	<b>2605</b>	<b>2705</b>	<b>2805</b>
CATEGORY	HS	UHS	UHS	UHS
MIXING RATIO	2:1	2:1	2:1	2:1
DESCRIPTION	<b>ANTI-SCRATCH</b>	<b>TOP CLEAR</b>	<b>ULTRA RAPID</b>	<b>ANTI-DRIP</b>
KEY FACTS	<p>SPECIAL FINISH ACCORDING TO VOC REGULATION</p> <p>EASY TO SPRAY</p> <p>HIGH GLOSS</p> <p>PARTIAL/COMPLETE REPAIRS</p>	<p>EASY TO SPRAY</p> <p>HIGH GLOSS</p> <p>PARTIAL/COMPLETE REPAIRS</p>	<p>EASY TO SPRAY</p> <p>HIGH GLOSS</p> <p>EXTRA FAST DRYING</p> <p>PARTIAL REPAIRS</p>	<p> shake well</p> <p>SAG CONTROL AGENT INSIDE</p> <p>PREMIUM GLOSS</p> <p>PARTIAL/COMPLETE REPAIRS ON HIGH STAND CARS</p>
CORRESPONDING HARDENERS	<p>4025 - ULTRAFAST</p> <p>4125 - FAST</p> <p>4225 - NORMAL</p> <p>4325 - SLOW</p>		<p>4525 - FAST</p> <p>4425 - NORMAL</p> <p>4625 - SLOW</p>	
AUTOMOTIVE VOC COMPLIANT DILUTION	5%-10%	0%	0%	0%
EXTRA AUTOMOTIVE NO VOC COMPLIANT DILUTION	max 18%	max 15%	max 10%	10%-20%
HANDS AND FLASH OFF	1 + 1 5'-10'	1/2 + 1 10'-15'	1/2 + 1 or 1/2+1+1 5'-10'	1/2 + 1 10'-15'
DRYING TIME	8h. at 20°C 30' at 60°C	8h. at 20°C 30' at 60°C	1h. + 1h. at 20°C 10' at 50°C	8h.+ 16h. at 20°C 25' at 60°C + 30' at 20°